

AUBURN PRODUCT NEWS

Auburn Manufacturing Company

29 Stack Street, Middletown, CT 06457

Customer Service: (800) 427-5387

Tel: (860) 346-6677 Fax: (860) 346-1334

website: www.auburn-mfg.com ◀◀ [Click Link to Learn More](#)

e-mail: info@auburn-mfg.com

SAE F-11 WOOL FELT (Typical Properties)

F-11 Felt is used for dryer seals, dust shields, gaskets, fluid storage seals, grommets, impregnated packings, spacers, washers and weatherstripping gaskets. **F-11 Felt** is 87% wool, light in weight, and easy to die-cut into specific shapes. **F-11 Felt** readily accepts pressure-sensitive adhesive. Sheets or rolls, in addition to die-cut parts, are available either plain or with an adhesive-backing applied to one or both sides. **F-11 Felt** can be supplied in any thickness between 1/64" and 4.00". **F-11 Felt's** standard color is grey.

Commercial Standard Grade

SAE Number

9R2

F-11

NTA Number

18R2

General Properties

Wool Content (fiber basis), min. %	87
Density (1") , lbs/sq yd	8.48
Standard Thickness Range, in.	1/64" thru 4.00"
Standard Width, in.	72
Color	Grey

Physical Properties

Specific Gravity (%)	18
Therm. Cond. (70F), btu/hr/sq ft/°F/in.	0.24
Thermal Expansion	0
Air Perm (1/16"), cfm/sq ft/0.5"H ₂ O	75-150
Liquid Absorption	% by weight (1.0 sp gr) By volume
	>375 88
Capillary (wicking height, 575 SSU, 70°F). in.	2.5
Coef. of Friction	0.37
Vibration Absorption	static load bearing cap/unit area dynamic stress endurance
	Low High-Medium
Noise Reduction Coef. (1")	0.64

Mechanical Properties

Tensile Strength (min), psi	200
Elongation (100 psi), %	35
Mullen Bursting Strength (1/8"), psi	60
Split Resistance (min.), lb/2" width	6
Hardness Range, Shore A	15-25
Compressibility(10% Deflection), psi	4
Recovery (within 1 min. after 10% deflection)	99
Abrasion Resistance	Fair

Chemical and Environmental Properties

Effect of Sunlight and Oxidation	None
Solvent Resistance and Stability in Oil	Excellent
Acid Resistance	dilute concentrated
	Excellent Fair
Alkali Resistance	dilute concentrated
	Fair Low
Temperature Range, °F	- 80 to +200

Auburn has more than 250 different gasket materials in stock for your immediate delivery!

Considering Diecut Parts

[Gaskets and Seals](#)
[Cushions, Pads, & Bumpers](#)
[Die-Cut Shapes](#)
[Adhesive-Backed Gaskets](#)

Explore Soft Gasket Materials

[Full Gasket Material List](#)
[Product Data Sheets](#)
[High Temperature Gasketing](#)
[Sponge & Foam Materials](#)

View Products & Services

[Custom Part Categories](#)
[Manufacturing Capabilities](#)
[Company Overview](#)
[Quality Policy](#)